

PERFORMANCE COATINGS
Powder Properties

Chemical composition:	Architectural grade TGIC free polyester
Health and Safety:	Refer to AVACE TGIC free polyester powder coating MSDS
Specification:	Complies with Qualicoat Class 1 BS EN 12206 BS 6496 & BS6497 BS476 Part 6 Fire propagation class 0 BS476 Part 7 Spread of flame class 1
Colours and finishes:	Powders are available from stock in a range of RAL & BS colours. Pantone, NCS, Designer RAL, Munsell colours 20kg make to order in 4 days.
Gloss level:	Solid Colours 25% +/- 5 units (60 degree head gloss meter)
Storage:	The product has a shelf life of 12 months if stored in its original packing in a fresh and dry environment at a temperature below 30°C
Cure Conditions:	Standard conditions are the following (actual temperature of the substrate): 15 minutes curing at 180°C 12 minutes curing at 190°C 10 minutes curing at 200°C
Application method:	Powder can be applied with corona electrostatic guns or tribo electric guns.
Specific weight:	1.3-1.6 Kg/dm ³ (depending on type and colour)
Particle size:	Suitable for electrostatic applications
Optimum film thickness:	Smooth: 40 to 60µm. The thickness of the coating film of certain strong colours may require to be higher in order to guarantee full opacity.
Product coverage:	Theoretical Coverage sqm/kg = 1000/ (average dft in µm x Specific wt in kg/ dm ³)
Pre-treatment:	To ensure maximum adhesion the substrate must be thoroughly clean, free from grease, oil, rust, mill scale or any other contaminant. Cleaning maybe carried out either by shot blasting, solvent or chemical degreasing. For applications where high corrosion or chemical resistance is required the substrate should be chemically treated prior to powder coating: Ferrous substrates: Zinc phosphate Zinc Coated steel: Zinc phosphate or Chromate conversion Aluminium: Chromate conversion

Mechanical and Chemical Properties

Test Thickness:	65 ± 10µm	UNI EN ISO 2360:2004
Adhesion:	GTO (equivalent to 5B according to ASTM D3359)	UNI EN ISO 2409:1996
Pencil hardness:	H-2H	ASTM D3363-00
Impact Test:	≥2.5Nm	ASTM D2794-93
Bending:	5mm	UNI EN ISO 6860:1996
Erichsen:	≥5 mm (no detachments, no cracks)	EN ISO 1520:1995
Hardness Buchholz:	≥80	EN ISO 2815:1998
Salt spray resistance:	1000hrs (≤ 3mm)	ASTM B117-97
Acetic acid salt spray:	1000hrs (≤ 4mm)	ISO 9227:1990
Humidity resistance:	1000hrs	DIN 50017:1982
Q-Uva (340 nm):	200hrs (loss of gloss<50%)	ASTM G154-00
Kesternich corrosion:	> 24 cycles (≤1mm)	EN ISO 3231:1997
Chemical Resistance:	Good resistance to diluted acids, alkali and oils at normal temperatures.	

Disclaimer

The information reported herein is not exhaustive. Use of the product for purposes or uses other than those it was designed for, without prior written authorisation of Avace Ltd. is done solely under the user's responsibility. Avace Ltd. takes all care to verify that all advice and directives concerning the product indicated in the relevant reports or verbally conveyed by its personnel are correct and applicable. Nevertheless, Avace Ltd. is not responsible for the conditions of the substrate or of numerous other factors that may affect the final performance of the product. Without a prior written agreement we cannot accept any responsibility of any of our products for damage or loss (including injury or death) due to improper use of the product. All information contained in the report is subject to future modifications consequent to continuous development of our expertise and to our policy of constantly improving our products and therefore is not binding.